



Topcoat Anti Slip Hard Wearing Anti-Slip Resin Floor Screed.

Topcoat Anti slip is a high performance 100% solids 2 component, Epoxy floor coating. It provides a hard wearing anti slip floor finish for use in most industrial and commercial premises where a high quality floor is required.

APPLICATIONS

Fire stations, Workshops, Processing areas, Corridors, Laboratory areas, Warehouses etc.

SURFACE PREPARATION

The surface should be free of grease, fat, laitance, loose materials, dust and release agents. These contaminants can be removed by washing with an industrial detergent followed by dust free shot blasting or diamond grinding.

MIXING INSTRUCTIONS

Mix thoroughly, the resin and hardener together until colour is uniform. Continue mixing for a further two minutes. Paddle mixer is preferred.

COVERAGE

One coat is sufficient for light traffic areas. Where the concrete is rough or in medium traffic areas a second coat is recommended. One 10kg. unit will cover approx 50 m² depending on surface conditions.

HEALTH & SAFETY

Skin and eye contact should be avoided by use of suitable protective clothing such as gloves, goggles, apron etc. Use in well ventilated area. In the event of eye contact flush with water for 15 minutes and seek medical attention.

TECHNICAL DATA

Standard Colours	Battleship Grey, Gunmetal Grey, Sand Yellow, Honey Yellow, Tile Red, Tomato Red, Marine Blue, Sky Blue, Leaf Green.
------------------	--

Volume Solids	100%
---------------	------

Pot Life @ 25 ⁰ C	30 min
------------------------------	--------

Packaging	10 Kg.
-----------	--------

Mixing Ratio

Volume-Resin: Hardener	3 :1
------------------------	------

Weight- Resin; Hardener	4:1
-------------------------	-----

Shelf life (sealed original container)	12 months.
---	------------

Storage Conditions	5 - 40 ⁰ C
--------------------	-----------------------

Application temperature	12 ⁰ C - 35 ⁰ C
-------------------------	---------------------------------------

Service Time - Foot Traffic	24 Hours
-----------------------------	----------

Recoat time	24 hours
-------------	----------

**Conforms to British Slip Resistance Standard
No. BS903: Part A26 under both wet & dry conditions.**